

rPET WSS03G

Recycled Polyethylene Terephthalate WSS03G

TECHNICAL DATASHEET

Product Description

rPET WSS03G is the reheat-efficient PET resin.

- Good Processability
- Low acetaldehyde content
- Uses: Thermoforming, fiber
- Application: Injection, injection stretch blow molding, filament.

Property	Test method	Value	Unit
Physical			
Intrinsic Viscosity (IV)	ASTM D1238	0.7 ± 0.02	dl/g
Bulk density	Internal method	≥ 800	kg/m ³
Pellet shape	Internal method	oval	
Pellet weight	Internal method	1.5 ± 0.5	g/100pellets
Thermal			
Melt Temperature	ASTM D3418	245 ± 5	°C
Other (visual, odor)			
Color	Visual inspection	Light blue	
	Spectrophotometer	L= 69 ± 3	
	Spectrophotometer	b = - 6 ± 4	
Acetaldehyde	HS GC/MS	≤ 1	ppm
Regulatory			
Food contact approval	US FDA 21 CFR Part 177.1630, EN 10/2011, QCVN 12-1:2011 BYT		
Contains no substance on the REACH 223 SVHC list			

Date of issue: August 5, 2022

Version:02